



## Handling maxit mörtel pad eco

**1**


maxit mörtel pad eco should only be removed from the manufacturer's packaging immediately before laying. All opened packages must be finished on the same day. The product must always be stored in a dry place and protected from moisture.

**2**


The bearing surfaces of the bricks must be moistened with water before placing the mortar pads in order to remove the grinding dust from the bricks.

**3**


Place the mortar pads flush with each other on the previously moistened brick bearing surfaces.

**4**

Water the maxit mörtel pad eco mortar pads with a watering device recommended by the manufacturer until the "troughs" on the surface of the pads are **completely** filled.

**5**

Once the added water has visibly soaked into the mortar pad so that the maxit mörtel pad eco has turned into a pulpy mortar mass, the stone must be placed after **a min. of 30 seconds** and **a max. of 3 minutes**, depending on the ambient climate.

**6**

The stone must then be levelled with a rubber mallet and worked into the mortar bed.